

® = registered trademark of BASF SE

# Uvinul® 3039

## Liquid Cyanoacrylate UV Absorber

### Characterization

Uvinul 3039 is a liquid ultraviolet light absorber (UVA) of the cyanoacrylate class, imparting excellent light stability to a variety of polymers.


### Chemical name

(2-ethylhexyl)-2-cyano-3,3-diphenyl acrylate

### CAS number

6197-30-4

### Chemical formula



### Molecular weight

361 g/mol

### Applications

Due to its good compatibility with plasticizers, Uvinul 3039 is particularly suitable for the stabilization of PVC-p and PVC plastisols. It can also be used in PUR, polyesters and PMMA.

### Product forms

Slightly yellowish, clear liquid

### Guidelines for use

Use levels of Uvinul 3039 range between 0.1 and 1.0 %, depending on substrate and performance requirements of the final application. Uvinul 3039 can be used alone or in combination with other functional additives such as antioxidants (hindered phenols, phosphites) and HALS light stabilizers, where often a synergistic performance is observed. Extensive performance data of Uvinul 3039 alone or in combination with other additives are available in many of the substrates listed above.

**Physical Properties**

Melting Point	-8 °C
Specific Gravity (20 °C)	1.05 g/ml

**Solubility (20 °C)**


Ethyl acetate	miscible
Methanol	miscible
Methyl ethyl ketone	miscible
Toluene	miscible
Water	<0.01

**g/100 g solution****Volatility** (pure substance; TGA, heating rate 20 °C/min in air)

Weight Loss %	Temperature °C
1.0	220
5.0	265
10.0	285

**Absorbance spectrum**

(10 mg/l, Chloroform)



*Uvinul 3039 exhibits high absorbance in the 280–320 nm region and no absorbance in the visible region (>400 nm) of the spectrum. The absorbance maximum is at 306 nm in chloroform solution.*

**Handling & Safety**

Uvinul 3039 exhibits a very low order of oral toxicity and does not present any abnormal problems in its handling or general use.

Detailed information on handling and any precautions to be observed in the use of the product(s) described in this leaflet can be found in our relevant health and safety information sheet.

**Note**

The descriptions, designs, data and information contained herein are presented in good faith, and are based on BASF's current knowledge and experience. They are provided for guidance only, and do not constitute the agreed contractual quality of the product or a part of BASF's terms and conditions of sale. Because many factors may affect processing or application/use of the product, BASF recommends that the reader carry out its own investigations and tests to determine the suitability of a product for its particular purpose prior to use. It is the responsibility of the recipient of product to ensure that any proprietary rights and existing laws and legislation are observed. No warranties of any kind, either expressed or implied, including, but not limited to, warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth herein, or that the products, descriptions, designs, data or information may be used without infringing the intellectual property rights of others. Any descriptions, designs, data and information given in this publication may change without prior information. The descriptions, designs, data and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

August 2010

BASF Schweiz AG  
Performance Chemicals/Plastic Additives  
Klybeckstrasse 141  
4057 Basel, Switzerland