

® = registered Trademark of BASF SE

# Tinuvin® 329

## Benzotriazole UV Absorber

### Characterization

Tinuvin 329 is an ultraviolet light absorber (UVA) of the hydroxyphenyl benzotriazole class, which is used as a light stabilizer for plastics and other organic substrates.


### Chemical name

2Phenol, 2-(2H-benzotriazol-2-yl)-4-(1,1,3,3-tetramethylbutyl)

### CAS number

3147-75-9

### Chemical formula



### Molecular weight

323 g/mol

### Applications

Tinuvin 329 is an effective light stabilizer for a variety of plastics and other organic substrates.

### Features/benefits

Tinuvin 329 protects polymers from UV radiation, helping to preserve the original appearance and physical integrity of molded articles, films, sheets, and fibers during outdoor weathering.

### Product forms

Tinuvin 329	Slightly yellow powder
Tinuvin 329 FL	Slightly yellow, rodlike granules

### Guidelines for use

The use levels of Tinuvin 329 range between 0.1 and 1.0 %, depending on substrate and performance requirements of the final application. The product can be used alone or in combination with other additives such as light stabilizers (hindered amines), antioxidants (hindered phenols, phosphites, thiosynergists, hydroxylamines), and other functional stabilizers and additives. The use of Tinuvin 329 in combination with hindered amine light stabilizers is particularly noteworthy in that a synergistic performance is often observed. Performance data of Tinuvin 329 alone or in combination with other additives are available in selected substrates.


**Physical Properties**

Melting Range	103–105 °C
Flashpoint	> 150 °C
Density (20 °C)	1.18 g/ml
Vapor Pressure (25 °C)	1 E-5 Pa

<b>Solubility (20 °C)</b>	<b>g/100 g solution</b>
Acetone	9
Benzene	32
Chloroform	37
Cyclohexane	15
Ethyl acetate	15
n-Hexane	6
Methanol	0.6
Water	<0.01

**Volatility** (pure substance; TGA, heating rate 20 °C/min in air)

Weight Loss %	Temperature °C
1.0	180
2.0	200
5.0	220

**Absorbance spectrum**  
(10 mg/l, Chloroform)

*Tinuvin 329 exhibits strong absorbance in the 300–400 nm region and minimal absorbance in the visible region (> 400 nm) of the spectrum. The absorption maxima are at 301 nm and 343 nm ( $\epsilon = 15910 \text{ l/mol}\cdot\text{cm}$ ) in chloroform solution.*

**Handling & Safety**

Tinuvin 329 exhibits a very low order of oral toxicity and does not present any abnormal problems in its handling or general use.

Detailed information on handling and any precautions to be observed in the use of the product(s) described in this leaflet can be found in our relevant health and safety information sheet.

**Note**

The descriptions, designs, data and information contained herein are presented in good faith, and are based on BASF's current knowledge and experience. They are provided for guidance only, and do not constitute the agreed contractual quality of the product or a part of BASF's terms and conditions of sale. Because many factors may affect processing or application/use of the product, BASF recommends that the reader carry out its own investigations and tests to determine the suitability of a product for its particular purpose prior to use. It is the responsibility of the recipient of product to ensure that any proprietary rights and existing laws and legislation are observed. No warranties of any kind, either expressed or implied, including, but not limited to, warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth herein, or that the products, descriptions, designs, data or information may be used without infringing the intellectual property rights of others. Any descriptions, designs, data and information given in this publication may change without prior information. The descriptions, designs, data and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

March 2011

BASF Schweiz AG  
Performance Chemicals/Plastic Additives  
Klybeckstrasse 141  
4057 Basel, Switzerland

