

® = registered trademark of BASF SE

# Irganox<sup>®</sup> PS 802

## Thiosynergic heat stabilizer

### Characterization

Irganox PS 802 is a dialkyl ester of thiodipropionic acid. It is used as a heat stabilizer in combination with a phenolic antioxidant.


### Chemical name

3,3'-Thiodipropionic acid dioctadecylester.

### CAS number

693-36-7

### Chemical formula



### Molecular weight

683 g/mol

### Applications

- Polymer materials requiring long-term thermal stability
- Polyethylene power cables
- XLPE power cables
- HDPE pipe
- Polypropylene
- Polyolefin under-the-hood automotive applications
- Styrene homo- and copolymers
- Adhesives

### Features/benefits

Irganox PS 802 used in combination with a primary phenolic antioxidant provides long-term heat stabilization to polymeric materials. With the lowest volatility of all BASF thiosynergists, it combines excellent performance with low odor.

### Product forms

Irganox PS 802 FL                      white to slightly yellow flake

### Guidelines for use

In general Irganox PS 802 can be used to improve the long-term heat stability of polymers at recommended levels of 0.05 % – 1 %. In peroxide cross-linked power cables, 0.02 % – 0.03 % Irganox PS 802 in combination with 0.02 % – 0.03 % Irganox 1035.

**Physical properties**

Melting range	64–67 °C
Flashpoint	257 °C
Vapor pressure (20 °C)	6.6 E-6 Pa
Specific gravity	0.98 g/ml
Bulk density	
FL	400–450 g/l

**Solubility (20 °C)**

	<b>g/100 g Solution</b>
Acetone	1
Chloroform	20
Ethanol	1.5
Ethyl acetate	1.7
n-Hexane	1.8
Methanol	1
Methylene chloride	13
Toluene	10
Water	<0.01

**Health & Safety**

Irganox PS 802 exhibits a very low order of oral toxicity and does not present any abnormal problems in its handling or general use.

Detailed information on handling and any precautions to be observed in the use of the product(s) described in this leaflet can be found in our relevant health and safety information sheet.

**Note**

The descriptions, designs, data and information contained herein are presented in good faith, and are based on BASF's current knowledge and experience. They are provided for guidance only, and do not constitute the agreed contractual quality of the product or a part of BASF's terms and conditions of sale. Because many factors may affect processing or application/use of the product, BASF recommends that the reader carry out its own investigations and tests to determine the suitability of a product for its particular purpose prior to use. It is the responsibility of the recipient of product to ensure that any proprietary rights and existing laws and legislation are observed. No warranties of any kind, either expressed or implied, including, but not limited to, warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth herein, or that the products, descriptions, designs, data or information may be used without infringing the intellectual property rights of others. Any descriptions, designs, data and information given in this publication may change without prior information. The descriptions, designs, data and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

September 2010

BASF Schweiz AG  
 Plastic Additives  
 4057 Basel, Switzerland  
[www.performancechemicals.basf.com](http://www.performancechemicals.basf.com)