

® = registered Trademark of BASF SE

Irganox® B 900

Synergistic processing and long-term thermal stabilizer system

Characterization

Irganox B 900 – a processing and long-term thermal stabilizer system – is a synergistic blend of 80 % Irgafos 168 and 20 % Irganox 1076.


Chemical name

Irgafos® 168 Tris(2,4-di-tert.-butylphenyl)phosphite
Irganox 1076 Octadecyl-3-(3,5-di-tert.-butyl-4-hydroxyphenyl)-propionate


CAS number

Preparation

Chemical formula



Irgafos 168



Irganox 1076

Applications

Irganox B 900 is mainly used in polyethylene and ethylene co-polymers, such as ethylene-vinylacetate copolymers. The blend can also be used in other polymers such as engineering plastics e. g. polycarbonates, polyesters, styrene homo- and copolymers, polyurethanes, elastomers, as well as adhesives and other organic substrates. Irganox B 900 can be used in combination with light stabilizers of the Tinuvin®, Uvinul® and Chimassorb® range.

Features/benefits

Irganox B 900 is a convenient blend addressing a range of stabilization needs. The relatively high phosphite content addresses applications with demanding processing conditions. In the recommended applications Irganox B 900 provides significant benefits, such as

- maintaining the original melt flow
- low color formation
- long-term thermal stability

Product forms

Irganox B 900	white, free-flowing powder
Irganox B 900 FF	white, free-flowing granules

Physical Properties

Bulk density	
Powder	530–630 g/l
FF	480–570 g/l

Health & Safety

Detailed information on handling and any precautions to be observed in the use of the product(s) described in this leaflet can be found in our relevant health and safety information sheet.

Note

The descriptions, designs, data and information contained herein are presented in good faith, and are based on BASF's current knowledge and experience. They are provided for guidance only, and do not constitute the agreed contractual quality of the product or a part of BASF's terms and conditions of sale. Because many factors may affect processing or application/use of the product, BASF recommends that the reader carry out its own investigations and tests to determine the suitability of a product for its particular purpose prior to use. It is the responsibility of the recipient of product to ensure that any proprietary rights and existing laws and legislation are observed. No warranties of any kind, either expressed or implied, including, but not limited to, warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth herein, or that the products, descriptions, designs, data or information may be used without infringing the intellectual property rights of others. Any descriptions, designs, data and information given in this publication may change without prior information. The descriptions, designs, data and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

June 2011

BASF Schweiz AG
Performance Chemicals/Plastic Additives
Klybeckstrasse 141
4057 Basel, Switzerland